

TÜV Rheinland LGA Products GmbH · 51101 Cologne

Sanwil Polska Sp. z o.o.
Monika Jasina
ul. Lwowska 52
37-700 Przemysl
POLAND

Contact
E-mail
Phone
Fax
Cologne,

Petra Van Dyck
Petra.Van.Dyck@de.tuv.com
+49 221/806-2129
+49 221/806-2882
29.01.2015

Report No. 0003134446/30 AZ193489

Test item: One fabric

Identification: Fabric: SANWIA

Condition at delivery: No claim


Date of delivery: 22.01.2015


Place of testing: Cologne, Nuremberg

Test period: 23.01.2015 to 29.01.2015

Test scope: Parameters selected by customer

Cologne, 29.01.2015


Dipl.-Ing. Gunther Bier
(Expert)


Petra Van Dyck
(Expert)

The test results exclusively refer to the samples examined.

This report shall not be reproduced except in full without written approval and does not authorize the use of a TÜV Rheinland Group label.

TÜV Rheinland LGA Products GmbH, Tillystr. 2, D-90431 Nuremberg, Tel +49 911 655 5225, Fax +49 911 655 5226, Mail service@de.tuv.com, Web www.tuv.com
Board of Management: Dipl.-Ing. Jörg Mähler, Dipl.-Kfm. Dr. Jörg Schlösser, Amtsgericht Nürnberg HRB 26013, VAT-No: DE811835490

Report No.: 0003134446/30 AZ193489

Date: 29.01.2015

2. Results

EN 71-3, Migration of certain elements, category 3

Sample No.	193489-001		
Sample composition	Art. 1		
Unit	mg/kg		
Soluble heavy metals			
Aluminium	<100		
Antimony	<5		
Arsenic	<1		
Barium	<100		
Boron	<10		
Cadmium	<0,1		
Chromium, total	<0,2		
Chromium (III)	<0,2		
Chromium(VI)	<0,2		
Cobalt	<1		
Copper	<10		
Lead	<1		
Manganese	<100		
Mercury	<1		
Nickel	<10		
Selenium	<5		
Strontium	<100		
Tin*	<3		
Zinc	<100		

Legal limit values according to Directive 2009/48/EC:

Category 3:

Scraped-off toy material

aluminium 70000 mg/kg, antimony 560 mg/kg, arsenic 47 mg/kg, barium 18750 mg/kg, boron 15000 mg/kg, cadmium 17 mg/kg, chromium(III) 460 mg/kg, chromium(VI) 0,2 mg/kg, cobalt 130 mg/kg, copper 7700 mg/kg, lead 160 mg/kg, manganese 15000 mg/kg, mercury 94 mg/kg, nickel 930 mg/kg, selenium 460 mg/kg, strontium 56000 mg/kg, tin 180000 mg/kg, zinc 46000 mg/kg

*Tin: If the migration of tin is less than the reporting limit the compliance with the limit value of 12 mg/kg can be confirmed. The determination of tin-organic compounds is not required in regards to metals and all-mineral materials like glass, ceramics etc.

Report No.: 0003134446/30 AZ193489
Date: 29.01.2015

Plasticizer

Sample No.	193489-002		
Sample composition	Art. 1		
Unit	%		
Phthalates			
Bis-(2-ethylhexyl)phthalate, DEHP	<0,01		
Dibutylphthalate, DBP	<0,01		
Benzylbutylphthalate, BBP	<0,01		
Sum DBP, BBP, DEHP	n.n.		
Diisononylphthalate, DINP	<0,01		
Diisodecylphthalate, DIDP	<0,01		
Di-n-octylphthalate, DNOP	<0,01		
Sum DNOP, DIDP, DINP	n.n.		

n.n. not detectable

Requirements according to regulation 1907/2006/EC Annex XVII respectively 2005/84/EC:
DEHP, DBP and BBP are totally banned (max. 0,1 % overall) in materials of toys and child care articles
DINP, DIDP and DNOP are banned (max. 0,1 % overall) in plasticised materials of toys and childcare articles which can be placed in the mouth by children.

----End of results----

Report No.: 0003134446/30 AZ193489
Date: 29.01.2015

3. Summary of methods

EN 71-3, Migration of certain elements, category 3	Standard: EN 71-3 + A1	Issue date: 01.10.14
---	-------------------------------	-----------------------------

Method description:

Safety of toys - Part 3: Migration of certain elements and chromium(VI) from toy materials of category III, analysis by ICP-MS according to DIN EN ISO 17294-2 respectively chromium(VI) after pre-column accumulation and post-column derivatisation by ion chromatography

Plasticizer

Method description:

In-house method - Determination of selected phthalates in toy material after solvent extraction, quantification by GC-MS

Notes:

Quantification equates the DIN EN ISO 18856.

This method also covers the phthalates and their maximum limits as requested by Section 10 of CPSIA of 2008 [H.R. 4040].